

## ETA-22/0756

### CHEFIX - FREE-PL



ETA-Danmark A/S  
Göteborg Plads 1  
DK-2150 Nordhavn  
Tel. +45 72 24 59 00  
Fax +45 72 24 59 04  
Internet www.etadanmark.dk

Authorised and notified according  
to Article 29 of the Regulation (EU)  
No 305/2011 of the European  
Parliament and of the Council of 9  
March 2011

MEMBER OF EOTA



### European Technical Assessment ETA-22/0756 of 2022/11/07

I General Part

**Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: ETA-Danmark A/S**

**Trade name of the construction product:**

Polyester Resin without Styrene

**Product family to which the above construction product belongs:**

Bonded injection type anchor for use in masonry:  
sizes M6 to M12

**Manufacturer:**

Damesa  
C/Garraf 10-12 Polígono Industrial Pla de la  
Bruguera  
E-08211 Castellar del Vallès  
Internet www.damesa.com  
Factory Plant 1

**Manufacturing plant:**

Factory Plant 1

**This European Technical Assessment contains:**

22 pages including 17 annexes which form an  
integral part of the document

**This European Technical Assessment is issued in accordance with Regulation (EU) No 305/2011, on the basis of:**

EAD 330076-00-0604, Metal injection anchors for  
use in masonry

**This version replaces:**

## ETA-22/0756

### CHEFIX - FREE-PL

Page 2 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (except the confidential Annexes referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

# ETA-22/0756

## CHEFIX - FREE-PL

Page 3 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

### II SPECIFIC PART OF THE EUROPEAN TECHNICAL ASSESSMENT

#### 1 Technical description of product

##### Technical description of the product

The Polyester Resin without Styrene is a bonded anchor (injection type) for use in masonry consisting of a cartridge with Polyester Resin without Styrene injection mortar a perforated nylon sleeve, and an anchor rod with hexagon nut and washer in the range of M6, M8, M10 and M12.

The product specification is given in annex A.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and masonry.

The characteristic material values, dimensions and tolerances of the anchors not indicated in Annexes shall correspond to the respective values laid down in the technical documentation<sup>1</sup> of this European Technical Assessment.

#### 2 Specification of the intended use in accordance with the applicable European Assessment Document (hereinafter EAD)

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The provisions made in this European Technical Assessment are based on an assumed intended working life of the anchor of 50 years.

The indications given on the working life cannot be interpreted as a guarantee given by the producer or Assessment Body, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

<sup>1</sup> The technical documentation of this European Technical Assessment is deposited at ETA-Danmark and, as far as relevant for the tasks of the Notified bodies involved in the attestation of conformity procedure, is handed over to the notified bodies.

## ETA-22/0756

### CHEFIX - FREE-PL

Page 4 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

### 3 Performance of the product and references to the methods used for its assessment

#### 3.1 Characteristics of product

**Mechanical resistance and stability (BWR 1):**

The essential characteristics are detailed in the Annex C.

**Safety in case of fire (BWR 2):**

The essential characteristics are detailed in the Annex C.

**Hygiene, health and the environment (BWR3):**

No performance assessed

**Safety in use (BWR4):**

For basic requirement Safety in use the same criteria are valid for Basic Requirement Mechanical resistance and stability (BWR1).

Other Basic Requirements are not relevant.

#### 3.2 Methods of assessment

The assessment of fitness of the anchor for the intended use in relation to the requirements for mechanical resistance and stability and safety in use in the sense of the Basic Requirements 1 and 4 has been made in accordance with EAD 330076-00-0604, Metal injection anchors for use in masonry.

## ETA-22/0756

### CHEFIX - FREE-PL

Page 5 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

#### **4 Assessment and verification of constancy of performance (AVCP)**

##### **4.1 AVCP system**

According to the decision 1997/177/EC of the European Commission, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) is 1.

#### **5 Technical details necessary for the implementation of the AVCP system, as foreseen in the applicable EAD**

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at ETA-Danmark prior to CE marking.

Issued in Copenhagen on 2022-11-07 by



Thomas Bruun  
Managing Director, ETA-Danmark

# ETA-22/0756


## CHEFIX - FREE-PL

Page 6 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Cartridge: Polyester Resin without Styrene**

- A) Foil Bag Cartridge 165ml, 300ml.
- B) Coaxial Cartridge 380ml / 400 ml / 410 ml / 420ml
- C) Side by Side Cartridge 345ml, 825ml


Cartridge Print: Polyester Resin without Styrene  
 Including - Installation procedure, Production Batch code, Expiry Date, Storage conditions, Health & Safety warning, Gel & Cure time according to temperatures.




**Marking:**

Polyester Resin without Styrene  
 Batch code, either expiry date or manufacturing date with shelf life

**Mixer with hanger**



**Mixer**




<b>POLYESTER RESIN WITHOUT STYRENE</b>	<b>Annex A1</b> of European Technical Assessment ETA-22/0756
Product and intended use	

# ETA-22/0756


## CHEFIX - FREE-PL

Page 7 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

### Anchor application in solid masonry (brick n°1 according to Annex B9)



### Anchor application in hollow/perforated masonry with nylon sleeve (brick n°2 according to Annex B9)



**POLYESTER RESIN WITHOUT STYRENE**

Product and intended use (2)

**Annex A2**  
 of European  
 Technical Assessment  
 ETA-22/0756

# ETA-22/0756


## CHEFIX - FREE-PL

Page 8 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

### Injection Mortar: Polyester Resin without Styrene – Resin System


Plastic sleeve for hollow/perforated masonry: nominal dimensions and material

Resin sleeves are the effective way to create a fixing where there is a hollow void, such as for perforated bricks and blocks, or a more porous material for example blockwork. Resin is injected to fill the volume of the sleeve and then forced through the fine perforations once the metal fixing rod is inserted. This distributes the resin material into the fixing cavity, forming a solid joint between the resin, the sleeve and the fixing.



#### 65565 - Nylon Perforated Sleeve – 16 x 85

Nominal Diameter 16mm  
Nominal Length 85mm



#### 65580 - Nylon Perforated Sleeve – 12 x 80

Nominal Diameter 12mm  
Nominal Length 80mm

Table A1: Minimum curing time

Minimum base material temperature C°	Gel time (working time) In dry/wet concrete	Curing time in dry concrete	Curing time in wet concrete
0°C ☒ T <sub>base material</sub> < 10°C	20 min	90 min	180 min
10°C ☒ T <sub>base material</sub> < 20°C	9 min	60 min	120 min
20°C ☒ T <sub>base material</sub> < 30°C	5 min	30 min	60 min
30°C ☒ T <sub>base material</sub> ☒ 40°C	3 min	20 min	40 min

The temperature of the bond material must be ≥ 20°C

**POLYESTER RESIN WITHOUT STYRENE**


Plastic sleeve and curing times

**Annex A3**  
of European  
Technical Assessment  
ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 9 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07



**Table A2: Threaded rods materials**

Designation	Material
<b>Threaded rods made of zinc coated steel</b>	
Threaded rod M6 – M12	Strength class 4.6, 4.8, 5.6, 5.8, 8.8, 10.9 and 12.9 EN ISO 898-1 Steel galvanized $\geq 5\mu\text{m}$ EN ISO 4042 Hot dipped galvanized $\geq 45\mu\text{m}$ EN ISO 10684
Washer ISO 7089	Steel galvanized EN ISO 4042; hot dipped galvanized EN ISO 10684
Nut EN ISO 4032	Strength class 8 EN ISO 898-2 Steel galvanized $\geq 5\mu\text{m}$ EN ISO 4042 Hot dipped galvanized $\geq 45\mu\text{m}$ EN ISO 10684
<b>Threaded rods made of stainless steel</b>	
Threaded rod M6 – M12	Strength class A2 or A4 – 50, A2 or A4-70 and A4-80 EN ISO 3506-1;
Washer ISO 7089	Strength class A4-70 and A4-80 EN ISO 3506-1;
Nut EN ISO 4032	Strength class A4-70 and A4-80 EN ISO 3506-1;
<b>Threaded rods made of high corrosion resistant steel</b>	
Threaded rod M6 – M12	Strength class 70 or 80. High corrosion resistant steel 1.4529, 1.4565 EN 10088
Washer ISO 7089	High corrosion resistant steel 1.4529, 1.4565 EN 10088
Nut EN ISO 4032	Strength class 70 or 80 EN ISO 3506-2; High corrosion resistant steel 1.4529, 1.4565 EN 10088

Commercial standard threaded rods with:

- material and mechanical properties according to Table A2;
- confirmation of material and mechanical properties by inspection certificate 3.1 according to EN-10204:2004;
- marking of the threaded rod with the embedment depth.

**POLYESTER RESIN WITHOUT STYRENE**

Materials

**Annex A4**  
of European  
Technical Assessment  
ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 10 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Use:**

The anchors are intended to be used for anchorages for which requirements for mechanical resistance and stability and safety in use in the sense of the Basic Requirements 1 and 4 of Regulation 305/2011 (EU) shall be fulfilled and failure of anchorages made with these products would compromise the stability of the works, cause risk to human life and/or lead to considerable economic consequences.

**Anchors subject to:**

- Static and quasi-static loads: M6 to M12

**Base materials:**

- Solid masonry (use category b) or hollow or perforated masonry (use category c) according to Annex B9. The mortar strength class of the masonry has to be M 2,5 according to EN 998-2:2010 at minimum

**Temperature range:**

The anchors may be used in the following temperature range:

- (a) -40°C to +40°C (max. short term temperature +40°C and max. long term temperature +24°C)
- (b) -40°C to +80°C (max. short term temperature +80°C and max. long term temperature +50°C)

**Use conditions (Environmental conditions):**

Threaded rods:

- a) Carbon galvanized steel class 4.6, 4.8, 5.6, 5.8, 8.8, 10.9 or 12.9 according to EN ISO 898-1 for dry internal conditions.
- b) Stainless steel A2 or A4-50, A2 or A4-70, A4-80 and HCR class 70 and 80 for structures subject to external atmospheric exposure (including industrial and marine environment) and to permanently damp internal condition.

Nuts and washers:

Corresponding to anchor rod material above mentioned for the different environmental exposures.

**Installation:**

- Category w/w: installation into dry or wet environmental conditions.
- Perforation with a drilling machine

**Proposed design methods:**

- Static and quasi-static load: EOTA TR 054, Design Method A.

<b>POLYESTER RESIN WITHOUT STYRENE</b>	<b>Annex B1</b> of European Technical Assessment ETA-22/0756
Intended use - Specification	

## ETA-22/0756

### CHEFIX - FREE-PL

Page 11 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Table B1 Installation data for solid masonry**

Size		M6	M8	M10	M12
Nominal drilling diameter	$d_0$ [mm]	8	10	12	14
Maximum diameter hole in the fixture	$d_{fix}$ [mm]	7	9	12	14
Embedment depth	$h_{ef}$ [mm]	80	80	85	85
Depth of the drilling hole	$h_1$ [mm]	$h_{ef} + 5$ mm			
Torque moment	$T_{inst}$ [Nm]	2	2	2	2
Thickness to be fixed	$t_{fix,min}$ [mm]	> 0			
	$t_{fix,max}$ [mm]	< 1500			
Minimum spacing	$S_{min}$ [mm]	240	240	255	255
Minimum edge distance	$C_{min}$ [mm]	120	120	127.5	127.5

**Table B2: Installation data for hollow/perforated masonry**

Size		M6	M8	M10	M12
Plastic sleeve		12 x 80		16 x 85	
Nominal drilling diameter	$d_0$ [mm]	12	12	16	16
Maximum diameter hole in the fixture	$d_{fix}$ [mm]	7	9	12	14
Embedment depth	$h_{ef}$ [mm]	80	80	85	85
Depth of the drilling hole	$h_1$ [mm]	$h_{ef} + 5$ mm			
Torque moment	$T_{inst}$ [Nm]	1.5	1.5	1.5	1.5
Thickness to be fixed	$t_{fix,min}$ [mm]	> 0			
	$t_{fix,max}$ [mm]	< 1500			
Minimum spacing	$S_{min,  }$ [mm]	250	250	250	250
	$S_{min,\perp}$ [mm]	120	120	120	120
Minimum edge distance	$C_{min}$ [mm]	100	100	100	100

**POLYESTER RESIN WITHOUT STYRENE**

Intended use - data


**Annex B2**  
of European  
Technical Assessment  
ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 12 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

### Manual blower pump: nominal dimensions



190mm (240x190x300mm) - ( A ) : 240mm (overall) - ( B ) : 190mm (Body) - ( C ) : 300mm (Tube)	280mm (330x280x300mm) - ( A ) : 330mm (overall) - ( B ) : 280mm (Body) - ( C ) : 300mm (Tube)	400mm (420x370x350mm) Article no. 84106 - ( A ) : 420mm (overall) - ( B ) : 370mm (Body) - ( C ) : 350mm (Tube)
--	--	---

### Steel Wire Brushes

#### Art. No. Specification



	18 mm
	13 mm
	10 mm

Table B3: Brush diameter

Type of threaded rod			Use in solid masonry				Use in hollow/perforated masonry			
			M6	M8	M10	M12	M6	M8	M10	M12
d <sub>0</sub>	Nominal drill hole	[mm]	8	10	12	14	16	16	16	16
d <sub>b</sub>	Brush diameter	[mm]	10	10	13	13	18	18	18	18

**POLYESTER RESIN WITHOUT STYRENE**

Cleaning tools

**Annex B3**  
of European  
Technical Assessment  
ETA-22/0756

## ETA-22/0756

### CHEFIX - FREE-PL








Page 13 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

Resin injection pump details		
Image	Size Cartridge / Code	Type
	165 / 300ml 165 / 300 ml 10:1	Manual
	345 / 380 / 400 / 410 / 420ml 420 ml 10:1 345 ml 10:1	Manual
	165 / 300 / 345 / 380 / 400 / 410 / 420ml 165 / 300 ml 345ml 380 / 400 / 410 / 420 ml 7.4v Tool	Battery
	380 / 400 / 410 / 420 / 825ml 380 / 400 / 410 / 420 ml 825ml	Pneumatic
<b>POLYESTER RESIN WITHOUT STYRENE</b>		<b>Annex B4</b> of European Technical Assessment ETA-22/0756
Tools for injection		

# ETA-22/0756

## CHEFIX - FREE-PL






Page 14 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

Table B4 - parameters: drilling, hole cleaning and installation in solid brick work		
<b>Instructions for use</b>		
<b>Bore hole drilling</b>		
		Drill hole to the required embedment depth with a hammer drill set in rotation-hammer mode using an appropriately sized carbide drill bit.
<b>Bore hole cleaning</b> Just before setting an anchor, the bore hole must be free of dust and debris.		
<b>a) Manual air cleaning (MAC)</b>		
	X 4	The manual pump may be used for blowing out bore holes  Blow out at least 4 times from the back of the bore hole until return air stream is free of noticeable dust.
	X 4	Brush 4 times with the specified brush size (brush $\varnothing \geq$ bore hole $\varnothing$ , see Table B3) by inserting the steel brush to the back of the hole (if needed with an extension) in a twisting motion and removing it. The brush must produce natural resistance as it enters the bore hole. If not, the brush is too small and must be replaced with the proper brush diameter.
	X 4	Blow out again with manual pump at least 4 times until return air stream is free from noticeable dust.
<b>b) Compressed air cleaning (CAC)</b>		
	X 2	Blow 2 times from the back of the hole (if needed with a nozzle extension) over the hole length with oil-free compressed air (min. 6 bar at 6m <sup>3</sup> /h) until return air stream is free from noticeable dust.
	X 2	Brush 2 times with the specified brush size (brush $\varnothing \geq$ bore hole $\varnothing$ , see Table B3) by inserting the steel brush to the back of the hole (if needed with an extension) in a twisting motion and removing it. The brush must produce natural resistance as it enters the bore hole. If not, the brush is too small and must be replaced with the proper brush diameter.
	X 2	Blow out again with compressed air at least 2 times until return air stream is free from noticeable dust.
<b>POLYESTER RESIN WITHOUT STYRENE</b>		<b>Annex B5</b> of European Technical Assessment ETA-22/0756
Procedure for solid masonry (1)		

## ETA-22/0756

### CHEFIX - FREE-PL

Page 15 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07








Instructions for use	
	Remove the threaded cap from the cartridge. Cut open the foil bag below the clip if necessary.
	Tightly attach the mixing nozzle. Do not modify the mixer in any way. Make sure the mixing element is inside the mixer. Use only the supplied mixer. For every working interruption longer than the recommended working time (Table A1) as well as for new cartridges, a new static-mixer shall be used.
	Insert the cartridge into the dispenser gun.
	Discard the initial trigger pulls of adhesive. Depending on the size of the cartridge, an initial amount of adhesive mix must be discarded.  Discard quantities are – 10cm for all cartridges
Instructions for use	
	Insert the nozzle to the bottom of the hole and inject the resin until the hole is filled 75%
	Insert the anchor, slowly with a slight twisting motion into the hole. Remove excess resin and leave the fixing until minimum curing (loading) times has elapsed
<b>POLYESTER RESIN WITHOUT STYRENE</b>	
Procedure for solid masonry (2)	<b>Annex B6</b> of European Technical Assessment ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 16 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07






**Table B5 - parameters: drilling, hole cleaning and installation in hollow brick work**

Instructions for use		
<b>Bore hole drilling</b>		
		Drill hole to the required embedment depth with a hammer drill set in rotation-hammer mode using an appropriately sized carbide drill bit.
<b>Bore hole cleaning</b> Just before setting an anchor, the bore hole must be free of dust and debris.		
<b>a) Manual air cleaning (MAC)</b>		
	X 4	The manual pump may be used for blowing out bore holes Blow out at least 4 times from the back of the bore hole until return air stream is free of noticeable dust.
	X 4	Brush 4 times with the specified brush size (brush $\varnothing \geq$ bore hole $\varnothing$ , see Table) by inserting the steel brush to the back of the hole (if needed with an extension) in a twisting motion and removing it. The brush must produce natural resistance as it enters the bore hole. If not, the brush is too small and must be replaced with the proper brush diameter.
	X 4	Blow out again with manual pump at least 4 times until return air stream is free from noticeable dust.
<b>b) Compressed air cleaning (CAC)</b>		
	X 2	Blow 2 times from the back of the hole (if needed with a nozzle extension) over the hole length with oil-free compressed air (min. 6 bar at 6m³/h) until return air stream is free from noticeable dust.
	X 2	Brush 2 times with the specified brush size (brush $\varnothing \geq$ bore hole $\varnothing$ , see Table B3) by inserting the steel brush to the back of the hole (if needed with an extension) in a twisting motion and removing it. The brush must produce natural resistance as it enters the bore hole. If not, the brush is too small and must be replaced with the proper brush diameter.
	X 2	Blow out again with compressed air at least 2 times until return air stream is free from noticeable dust.
<b>POLYESTER RESIN WITHOUT STYRENE</b>		<b>Annex B7</b> of European Technical Assessment ETA-22/0756
Procedure for hollow/perforated masonry (1)		

# ETA-22/0756

## CHEFIX - FREE-PL


Page 17 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

Instructions for use	
	Remove the threaded cap from the cartridge without cutting. Cut open the foil bag below the clip if necessary.
	Tightly attach the mixing nozzle. Do not modify the mixer in any way. Make sure the mixing element is inside the mixer. Use only the supplied mixer with the adhesive. For every working interruption longer than the recommended working time (Table A1) as well as for new cartridges, a new static-mixer shall be used.
	Insert the cartridge into the dispenser. Press the release trigger to retract the plunger and insert the cartridge neatly into the cradle without any distortion.
	Discard the initial trigger pulls 10cm of adhesive. Resin will flow from the cartridge as soon as dispensing is initiated.
Instructions for use	
	Introduce the sleeve of suitable dimension (see table B2) to the back of the hole so that the collar is level with the hole face. The cap may be opened to allow full nozzle insertion.
	Insert the nozzle to the end of the sleeve and inject the resin until the sleeve is 100% filled. Close the cap.
	Insert the anchor, slowly with a slight twisting motion into the sleeve. Remove excess resin and leave the fixing until minimum curing (loading) times has elapsed
<b>POLYESTER RESIN WITHOUT STYRENE</b>	
Procedure for hollow/perforated masonry (2)	
<b>Annex B8</b> of European Technical Assessment ETA-22/0756	

# ETA-22/0756

## CHEFIX - FREE-PL

Page 18 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07




**Brick n.1**

Category b: Solid clay masonry:

**Mattone pieno UNI (12.6.25)**

Bulk density class  $\rho=1.6 \text{ kg/dm}^3$

Minimum compressive strength  $f_b=18 \text{ MPa}$



**Brick n.2**

Category c: Hollow masonry:

**Doppio UNI (12.12.25)**

Bulk density class  $\rho=0.9 \text{ kg/dm}^3$

Minimum compressive strength  $f_b=6.0 \text{ MPa}$

**POLYESTER RESIN WITHOUT STYRENE**

Type and dimensions of the brick

**Annex B9**  
 of European  
 Technical Assessment  
 ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 19 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Table C1: Design method A, characteristic tension and shear load values**

ESSENTIAL CHARACTERISTICS		PERFORMANCE			
Installation parameters		M6	M8	M10	M12
d	[mm]	6	8	10	12
d <sub>0</sub> category b (solid masonry)	[mm]	8	10	12	14
d <sub>0</sub> category c (hollow or perforated masonry)	[mm]	12	12	16	16
Type of plastic sleeve for use in category c		12x80	12x80	16x85	16x85
d <sub>fix</sub>	[mm]	7	9	12	14
h <sub>l</sub>	[mm]	h <sub>ef</sub> + 5 mm			
t <sub>fix</sub>	Min [mm]	> 0			
	Max [mm]	≤ 1500 mm			
T <sub>inst</sub> category b (solid masonry)	[Nm]	2	2	2	2
T <sub>inst</sub> category c (hollow or perforated masonry)	[Nm]	1.5	1.5	1.5	1.5
S <sub>min</sub> category b (solid masonry)	[mm]	240	240	255	255
C <sub>min</sub> category b (solid masonry)	[mm]	120	120	127.5	127.5
S <sub>min</sub> category c (hollow masonry) S <sub>min,  </sub>	[mm]	250	250	250	250
S <sub>min</sub> category c (hollow) S <sub>min,⊥</sub>	[mm]	120	120	120	120
C <sub>min</sub> category c (hollow masonry)	[mm]	100	100	100	100
<b>* Resistance for tensile and shear load</b>					
Temperature range -40°C/+40°C (T <sub>mp</sub> = 24°C)		M6	M8	M10	M12
Brick n°1 (solid)	N <sub>Rk</sub> [kN]	4	4	4	4
	V <sub>Rk</sub> [kN]	6	6	7	7
Brick n°2 (hollow)	N <sub>Rk</sub> [kN]	2	2	2	2
	V <sub>Rk</sub> [kN]	2	2	2	2
<b>* Resistance for tensile and shear load</b>					
Temperature range -40°C/+80°C (T <sub>mp</sub> = 50°C)		M6	M8	M10	M12
Brick n°1 (solid)	N <sub>Rk</sub> [kN]	3.5	3.5	3.5	3.5
	V <sub>Rk</sub> [kN]	6	6	7	7
Brick n°2 (hollow)	N <sub>Rk</sub> [kN]	1.5	1.5	1.5	1.5
	V <sub>Rk</sub> [kN]	2	2	2	2
<b>POLYESTER RESIN WITHOUT STYRENE</b>		<b>Annex C1</b> of European Technical Assessment ETA-22/0756			
Performance for static and quasi-static loads: Resistances					

# ETA-22/0756

## CHEFIX - FREE-PL

Page 20 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Table C2: Characteristic bending moments**

Size			M6	M8	M10	M12
Characteristic resistance with standard threaded rod grade 4.6	$M_{Rk,s}$	[Nm]	6	15	30	52
Partial safety factor	$\gamma_{Ms}$	[-]	1,67			
Characteristic resistance with standard threaded rod grade 5.8	$M_{Rk,s}$	[Nm]	8	19	37	66
Partial safety factor	$\gamma_{Ms}$	[-]	1,25			
Characteristic resistance with standard threaded rod grade 8.8	$M_{Rk,s}$	[Nm]	12	30	60	105
Characteristic resistance with standard threaded rod grade 10.9	$M_{Rk,s}$	[Nm]	15	37	75	131
Partial safety factor	$\gamma_{Ms}$	[-]	1,25			
Characteristic resistance with standard threaded rod stainless steel A2, A4-70 and HCR (class 70)	$M_{Rk,s}$	[Nm]	11	26	52	92
Partial safety factor	$\gamma_{Ms}$	[-]	1,56			
Characteristic resistance with standard threaded rod stainless steel A4-80 and HCR (class 80)	$M_{Rk,s}$	[Nm]	12	30	60	105
Partial safety factor	$\gamma_{Ms}$	[-]	1,33			

**Table C3: Characteristic values for tension and shear load.**

ESSENTIAL CHARACTERISTICS			PERFORMANCE			
<b>* Resistance for tensile and shear load</b>						
<b>Temperature range -40°C/+40°C (<math>T_{mlp} = 24°C</math>) and -40°C/+80°C (<math>T_{mlp} = 50°C</math>)</b>			<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>
$\gamma_{Mm}$ [-] Category w/w			2,50			
Brick n°1	$S_{cr,N}$	[mm]	240	240	255	255
	$C_{cr,N}$	[mm]	120	120	127,5	127,5
Brick n°2	$S_{cr,N,  }$	[mm]	250	250	250	250
	$S_{cr,N,\perp}$	[mm]	120	120	120	120
	$C_{cr,N}$	[mm]	100	100	100	100
<b><math>\beta</math> coefficient for in situ test (ETAG 029 Annex B)</b>			<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>
<b>Temperature range: -40°C/+40°C</b>						
Brick N° 1 - Solid brick	$\beta$	[-]	0,90	0,87	0,87	0,76
Brick N° 2 - Hollow/perforated brick	$\beta$	[-]	0,90	0,87	0,87	0,76
<b><math>\beta</math> coefficient for in situ test (ETAG 029 Annex B)</b>			<b>M6</b>	<b>M8</b>	<b>M10</b>	<b>M12</b>
<b>Temperature range: -40°C/+80°C</b>						
Brick N° 1 - Solid brick	$\beta$	[-]	0,73	0,70	0,70	0,62
Brick N° 2 - Hollow/perforated brick	$\beta$	[-]	0,73	0,70	0,70	0,62

POLYESTER RESIN WITHOUT STYRENE

Performance for static, quasi-static: Displacements

**Annex C2**  
of European  
Technical Assessment  
ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 21 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Table C3 cont.: Characteristic values for tension and shear load.**

Displacement under service load - Tensile load					
Temperature range -40°C/+40°C (T <sub>mlp</sub> = 24°C)					
Brick n°1 – Solid brick		M6	M8	M10	M12
Admissible service load in tensile	F [kN]	1,14			
Displacement	δ <sub>N0</sub> [mm]	0,09	0,09	0,04	0,04
	δ <sub>N∅</sub> [mm]	0,18	0,18	0,07	0,09
Brick n°2 – Hollow/perforated brick		M6 With sleeve	M8 With sleeve	M10 With sleeve	M12 With sleeve
Admissible service load in tensile	F [kN]	0,57			
Displacement	δ <sub>N0</sub> [mm]	0,10	0,17	0,17	0,14
	δ <sub>N∅</sub> [mm]	0,21	0,35	0,35	0,28
Temperature range -40°C/+80°C (T <sub>mlp</sub> = 50°C)					
Brick n°1 – Solid brick		M6	M8	M10	M12
Admissible service load in tensile	F [kN]	1,00			
Displacement	δ <sub>N0</sub> [mm]	0,08	0,08	0,03	0,04
	δ <sub>N∅</sub> [mm]	0,16	0,16	0,06	0,07
Brick n°2 – Hollow/perforated brick		M6 With sleeve	M8 With sleeve	M10 With sleeve	M12 With sleeve
Admissible service load in tensile	F [kN]	0,43			
Displacement	δ <sub>N0</sub> [mm]	0,08	0,13	0,13	0,10
	δ <sub>N∅</sub> [mm]	0,16	0,26	0,26	0,21
Displacement under service load Shear load					
Temperature range -40°C/+40°C (T <sub>mlp</sub> = 24°C)					
Brick n°1 – Solid brick		M6	M8	M10	M12
Admissible service load in shear	F [kN]	1,71		2,00	
Displacement	δ <sub>V0</sub> [mm]	0,97	0,97	1,03	0,58
	δ <sub>V∅</sub> [mm]	1,45	1,45	1,55	0,87
Brick n°2 – Hollow/perforated brick		M6 With sleeve	M8 With sleeve	M10 With sleeve	M12 With sleeve
Admissible service load in shear	F [kN]	0,57			
Displacement	δ <sub>V0</sub> [mm]	0,74	0,84	0,84	1,09
	δ <sub>V∅</sub> [mm]	1,11	1,26	1,26	1,64
Temperature range -40°C/+80°C (T <sub>mlp</sub> = 50°C)					
Brick n°1 – Solid brick		M6	M8	M10	M12
Admissible service load in shear	F [kN]	1,71		2,00	
Displacement	δ <sub>V0</sub> [mm]	0,97	0,97	1,03	0,58
	δ <sub>V∅</sub> [mm]	1,45	1,45	1,55	0,87
Brick n°2 – Hollow/perforated brick		M6 With sleeve	M8 With sleeve	M10 With sleeve	M12 With sleeve
Admissible service load in shear	F [kN]	0,57			
Displacement	δ <sub>V0</sub> [mm]	0,74	0,84	0,84	1,09
	δ <sub>V∅</sub> [mm]	1,11	1,26	1,26	1,64

POLYESTER RESIN WITHOUT STYRENE

Performance for static, quasi-static and seismic loads: Displacements

**Annex C3**  
of European  
Technical Assessment  
ETA-22/0756

# ETA-22/0756

## CHEFIX - FREE-PL

Page 22 of 22 of European Technical Assessment no. ETA-22/0756, issued on 2022-11-07

**Table C4: Reaction to fire.**

ESSENTIAL CHARACTERISTICS	PERFORMANCE
Reaction to fire	In the final application, the thickness of the mortar layer is about 1 to 2 mm and most of the mortar is material classified class A1 according to EC Decision 96/603/EC. Therefore, it may be assumed that the bonding material (synthetic mortar or a mixture of synthetic mortar and cementitious mortar) in connection with the metal anchor in the end use application do not make any contribution to fire growth or to the fully developed fire and they have no influence to the smoke hazard.

**Table C5: Resistance to fire.**

ESSENTIAL CHARACTERISTICS	PERFORMANCE
Resistance to fire	NPA

**POLYESTER RESIN WITHOUT STYRENE**

Performance for static, quasi-static and seismic loads: Fire reaction and resistance

**Annex C4**  
 of European  
 Technical Assessment  
 ETA-22/0756